

No.1110-01297-03

Grease for high temperature

MORESCO HIGREASE UM-1

◆ Description

MORESCO-HIGREASE UM-1 is the synthetic based Grease on alkyl-diphenyl-ether, which is prepared by MORESCO's unique synthesizing and refining technology, and suitable for the lubrication systems at high temperature.

MORESCO HIGREASE UM-1 is used for the lubrication of the bearing, for Textile machine and so on, which face at high temperature atmosphere, and its superior quality has been well recognized by customers.

◆ Characteristics

☆ *Excellent thermal stability and water-proof.*

☆ *The low friction coefficient is possessed in a wide-ranging temperature region and friction and the wear are decreased.*

☆ *The use of a long term is endured and easy maintenance.*

◆ General property

	MORESCO HIGREASE UM-1
Appearance	Yellow paste
Penetration 60W (25°C)	313
Dropping point °C	Over 260
Oil separation 30H (100°C)	1.4%
Oil separation 30H (150°C)	2.0%
Evaporation loss 22H (98.9°C)	0.35%
Copper strip corrosion 24H (100°C)	Passed

◆ How to use

High temperature lubrication part in drier roll bearing and other bearing etc. such as Textile machines and paper manufactures machines.

◆ Storage

Please refer to Material Safety Data Sheet (M.S.D.S.)

◆ Package

400g/ tube (6 tubes / ctn)

2.5kg/pail

16kg/pail

株式会社 **MORESCO** URL: <http://www.moresco.co.jp/>

東京支店 〒104-0028 東京都中央区八重洲2丁目8-5 菱進八重洲ビル8階 TEL03-3273-7526
大阪支店 〒541-0051 大阪市中央区備後町3丁目2-15 モレスコ本町ビル7階 TEL06-6262-3310
小山営業所 〒323-0022 栃木県小山市駅東通1丁目4-3 小山駅東口ビル2階 TEL0285-23-9372
名古屋営業所 〒460-0002 名古屋市中区丸の内1丁目15-9 第20KTビル10階 TEL052-222-3235
九州営業所 〒830-0044 福岡県久留米市本町4-33 明治安田生命久留米本町ビル3階 TEL0942-30-7734
研究センター 〒650-0047 神戸市中央区港島南町5丁目5-3 TEL078-303-9010
カスタマーセンター E-mail: customercenter@moresco.co.jp TEL06-6262-3385

MORESCO Corporation

Head Office : 5-5-3, Minatojimaminami-machi, Chuo-ku, Kobe-city, Hyogo, Japan, 650-0047
R&D Center Phone: 078-303-9010 Fax: 078-303-9020
Tokyo Branch: Ryoshinayasu-Bldg., 2-8-5, Yaesu, Chuo-ku, Tokyo, Japan, 104-0028
(International Business Division) Phone: 03-3273-7526 Fax: 03-3281-7756